

UHB Metallized PET Laminates with PST™ Coating For Vacuum Insulation Panels


Product Overview

Absolute barrier, negligible thermal bridge

The new range of metallized PET based ultra high barrier (UHB) laminates from Avery Dennison Hanita achieves the gas barrier levels of Aluminium foil, but without the detrimental thermal bridge of foil.

Based on a new Proprietary Surface Treatment (PST™) coating process that dramatically reduces permeation of atmospheric gasses, these metallized polyester (MPET) and sealable polyethylene laminates provide the answer for VIP panels in applications where ultra-high barrier to gas is critical.

Typical structure



The advantages:

- > Exceptional barrier to gas for increased longevity
- > Negligible thermal bridge
- > Highly cost-efficient
- > Eliminates need for getter, increasing savings
- > High thermal durability
- > No width limitations
- > High efficiency enables use of lower-performing core types

Applications

Avery Dennison Hanita metallized laminates with PST coating are designed for typical fiberglass core applications such as refrigeration or thermal packaging. Additionally, when high temperatures are involved in the application (for boilers, hot vending, rice cookers, district heating etc), the new PST films complement both fiberglass and fumed silica cores. In fact, thanks to their cost effective yet high resistance qualities, PST laminates open the door to using a wide range of alternative core types, from Perlite to PU.


- > VIPs for hot/cold vending machines
- > VIPs for long term cold shipping containers
- > VIPs for hot water tanks
- > VIPs for long term refrigeration/heater markets

Exceptional barrier performance


MPET laminates with PST coating feature an outstandingly low Gas Transmission Rate (GTR) of <math><3.0 \text{ [cc (STP)/ m}^2\text{/year]} \text{ @ } 22^\circ\text{C}/50\% \text{ RH}</math>. This combines with the superior metallization and MVTR performance (0.035gr/m²day @38°C/90%RH) of standard Avery Dennison Hanita MPET films, yet without the thermal bridge issues arising from use of Al-foil laminates.

The comparative gas barrier levels and thermal performance of different laminates can be seen in the graphs below:

Comparison of air permeability of different VIPs formed from various laminates, as per Arrhenius equation



Thermal Conductivity at 80°C, Initial and after 30 days (center of panel)



Please review the Storage Conditions and Sealing Parameter Technical Sheets.

Optimal conditions may vary according to equipment used.

For further information contact barrier.laminates@eu.averydennison.com

DISCLAIMER: All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see: [terms.averydennison.com](https://www.averydennison.com/terms)

©2018 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation and/or its Affiliates. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.