# LABEL FACE FILMS Printable Topcoated Polyester Films

#### Item number:

#### A02319P

### Description:

23 micron (1 mil) white metallized polyester film with print primer to optimize adhesion of printing inks and increase scuff resistance.

#### Applications:

Opaque Labels

#### Suitable for printing with:

- Rotogravure
- UV flexography
- Silkscreen
- UV Inkjet
- Thermal transfer (subject to ribbon compatibility)

### Product Specifications:

PROPERTY	TEST METHOD	A02319P	
Appearance		Opaque white	
Thickness	-	24 1	[micron] [mil]
Area Yield	-	28.4 20	[m²/kg] [msi/lb]
TLT	ASTM D-1003	<0.3	
Tensile Strength	ASTM D-882	MD <b>18</b> ± 5 <b>25600</b> ± 7100	TD 22 ± 5 [Kgf/mm <sup>2</sup> ] 31300 ± 7100 [psi]
Elongation at Break	ASTM D-882	MD <b>130</b> ± 30	TD <b>80</b> ± 30 [%]
Shrinkage	After 30 minutes at 150 °C	MD <b>1.5</b> ± 1.0	TD <b>0.5</b> ± 0.5 [%]









# LABEL FACE FILMS Printable Topcoated Polyester Films

DS No=2111/9, Page 2 of 2, January 2019

DISCLAIMER - All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see http://terms.europe.averydennison.com

©2019 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation and/or its Affiliates. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.

Avery Dennison Israel Ltd Kibbutz Hanita, 2288500 Israel T: +972 4 985 9919

E: hanita.coatings@eu.averydennison.com www.hanita.averydennison.com



