

LABEL FACE FILMS

“No-tack” Polyester Film

Item number: **K03654**

Description:

36-micron clear polyester film coated on the base side with a non-silicone dry peel layer, **featuring a print receptive topcoat** for conventional print and thermal transfer on the upper surface.

Suitable for printing with:

- Rotogravure
- UV Flexography
- UV letterpress
- Silkscreen
- UV Cure
- Thermal transfer (subject to ribbon compatibility)

Benefits

- No sticky residue
- Totally transparent
- Easily removable
- Good print adhesion

Applications:

- Coupon or redemption label base

Product Specifications:

PROPERTY	TEST METHOD	K03654	
Appearance	-	Clear	
Thickness	-	36 1.5	[micron] [mil]
Area Yield	-	19	[m ² /kg]
Tensile Strength	ASTM D-882	MD 22	TD 24 [Kgf/mm ²]
Elongation at Break	ASTM D-882	MD 165	TD 130 [%]
Shrinkage	After 30 minutes at 150 °C	MD 3	TD 1 [%]



LABEL FACE FILMS

“No-tack” Polyester Film

DS No=2800/1, Page 2 of 2, November 2018

DISCLAIMER - All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2018 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation and/or its Affiliates. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.

Avery Dennison Israel Ltd
Kibbutz Hanita, 2288500 Israel
T: +972 4 985 9919
E: hanita.coatings@eu.averydennison.com
www.hanita.averydennison.com

